



ㄱ	(가	~)	1
ㄴ	(~)	2
ㄷ	(~)	2
ㄹ	(~)	3
ㅁ	(())	~)	3
ㅂ	(~)	4
ㅅ	(~)	4
ㅇ	(~)	6
ㅈ	(~)	9
ㅊ	(~)	10
ㅋ	(~)	11
ㅌ	(~)	12
ㅍ	(~)	12
ㅎ	(~)	13
ETC	(S	A	E)
				14

천세산업주식회사

액명	분자식	농도(%)	금속					플라스틱(합성수지)						내마모재		고무							
			STS-304	STS-316	Ti(티타늄)	하스테로이C	Aluminum	PVC 영화비닐	PE 폴리에틸렌	PP 폴리프로필렌	PCTFE 3불화에틸렌	Teflon 테프론	PMMA 아크릴	족연(글루)	세라믹	CR 네오프렌	NBR 부니-N	CSM 하이파렌	EPDM E.P.R	FPM 바이톤			
가성소다 (수산화나트륨)	NaOH	dil	△ ○(b.p)	△ ○(b.p)	30% ○(100°C)	○(b.p)	×	○ ○(60°C)	○ ○(60°C)	○ ○(100°C)	10% ○(25°C)	○ ○(121°C)		○(b.p)	△	○(93°C)	○	○(93°C)	○	○(RT) ×(80°C)			
		conc.	○(130°C) ×(170°C)	○(130°C) ×(170°C)	80% ○(20°C)	○	×	○ ○(70°C)	○ ○(60°C)	○ ○(60°C)	50% ○(100°C)	○ ○(121°C)	○ ○(60°C)	○(260°C)	×	○(70°C)	○	○(104°C)	○	×			
가성칼리 (수산화칼륨)	KOH		○ ○(80°C)	○ ○(80°C)	○ ○(b.p)	○ ○(b.p)	×	○ ○(24°C)	○ ○(60°C)	○ ○(60°C)	○ ○(20°C)	○ ○(121°C)	○ ○(20°C)	○	△ ×	○	×	○	○	○ ○ △			
가솔린 (하이옥坦)	C4~C12 탄화수소혼합체	精製 鉛入	○(b.p)	○(b.p)	○(b.p)	○(b.p)	○	×	(60°C)	×	(24°C)	○(26°C)	○(24°C) ○(121°C)	×		○	×	○	×	○			
감서당액	—		○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○			
개미산 (포름산)	HCOOH	10	△	△	×	○	×	×	×	(60°C)	○	○(85°C)	○(25°C) 50%	○	○(20°C)	○	○	○	○	○	×	○	○(70°C)
		90	○(30°C) △(100°C) ×(b.p)	○(30°C) △(100°C) ×(b.p)	○	○(60°C)		○(30°C)	○(60°C)	○(80°C)	87% ○(133°C)	○(b.p)	×	(20°C)	○	○	○	○	○	○	○	○	
계로신	—													○(20°C)			×	○	×	△(150°C)			
겨자	—		○	○		○			○	○					○	○	○	○	○				
경유	—		○(b.p)	○(b.p)	○(b.p)	○(b.p)				○	○	○	○			○	○	○	○	○			
과당	C ₆ H ₁₂ O ₆		○	○	○	○		○(60°C)	○	○(80°C)	○	○	○	○(60°C)	○	○	○	○	○	○	○		
과망간산칼륨	KMnO ₄	10 10 10	○(100°C) ○(b.p)	○(100°C)		○	○(20°C)		○(60°C)	○	○5% ×		○	○(20°C) 1/10N	○	○	×	○	○	○	○	○	
과불산소다	NaBO ₃		△	△		△	×			○	○	○	○		○	○	○	○	○	×	○	○	
과산화바륨	BaO ₂	10	○(95°C)	○(95°C)										○									
과산화소다	Na ₂ O ₂		○	○	○	○	×	○	○	○	○	○	○	○	○	○	○	○	○	○	○		
과산화수소	H ₂ O ₂	10		○(30°C)				○	○(20°C)		30% △(20°C) △(85°C)	○(25°C)	○(20°C)		○40%	○40%					○40%		
		30 dil	○(30°C)	○(30°C)			50% ○(60°C)	○	○(20°C)	○	○(<50°C) ×(<50°C)	○	○(<50°C)	×	○(20°C)	○	○	×	○(24°C)	○(20°C)			
		80 90 conc.	△ ○ ×	○(50°C) ○ ○	○	○	○ ○	○	○(<50°C) ×(<50°C)	○ ○	○(<50°C)	○ ○	×	○(20°C)	○	△(<50°C) ×	○(<50°C) △ ○	○(<50°C) ○ ○	○(<50°C) ○ ○				
과산화칼륨	K ₂ O ₂	10	○(95°C)	○(95°C)																			
과염소산	HClO ₄	10 76.3	○(100°C)	○(100°C)	○(100°C)		×	○(60°C)	○(60°C)	○(70°C)		○	○		○	○	○(100°C) ×	○(100°C) ×	○	○	○		
과염소산소다	NaClO ₄	10	○(100°C)	○(100°C)	○(100°C)			○(60°C)	○(60°C)	○	○	○	○				○(100°C)	×	○	○	○		
과염소산암모늄	NH ₄ Cl ₄	10%	○(b.p)	○(100°C)	○(100°C)		×	○(60°C)	○(60°C)		○	○	○			○	○	○(100°C)					
과증	—		○	○		○	○		○	○		○	○		○	○	○	○	○	○	○	○	
과황산암모늄	(NH ₄) ₂ SO ₄		○	○		○		○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	
구연산	(CH ₂ · COOH) ₂ · C(CH ₃)COOH		△	○		○	×	○(60°C)	○	○(85°C)		○	○(20°C)	○	○	○	×	○	○	○	○	○	
과염소산칼륨	KClO ₄	10	○(100°C)	○(100°C)	○(100°C)	△		○(60°C)	○(60°C)		○	○			○	○	○(100°C)						
규불화수소	H ₂ SIF ₆	蒸氣	△ ○(100°C)	△ ○(100°C)	△ ×			<33% ○(60°C)	△ ○(60°C)		○	○	○		○	×	○	○(121°C)	○	○	○		
규산	SiOH ₂		○	○	○	○		○	○	○		○	○		○	○	○	○	○	○	○	○	

천세산업주식회사

액명	분자식	농도(%)	금속					플라스틱(합성수지)						내마모재		고무				
			STS-304	STS-316	Ti(티타늄)	하스테로이C	Aluminum	PVC 영화비닐	PE 폴리에틸렌	PP 폴리프로필렌	PCTFE 3불화에틸렌	Teflon 테프론	PMMA 아크릴	족연(글루)	세라믹	CR 네오프렌	NBR 부니-N	CSM 하이파렌	EPDM E.P.R	FPM 바이톤
규산소다(나트륨) (상영기)	NaSiO ₃ Na ₂ SiO ₂		○	○	○	○	×	○	○	○	○	○	○(60°C)	○	○	○	○	○	○	
규산칼륨	K ₂ SiO ₃												○(60°C)	○						
규소기름 (실리콘오일)	—		○	○	○	○	○	○	○	○		○	×			○	○	○	○	
그리스	—		○	○	○	○	○	○	○	○		○			○	○	○		○	
글리세린	(CH ₂ ·OH) ₂ CHOH	100 100	○(b.p.)	○(b.p.)	○(b.p.)	○(b.p.)	○	○(60°C)	○(60°C)	○(100°C)	○(160°C)	○	○(20°C)	○	○(b.p.)	○(70°C)	○	○(93°C)	○(121°C)	
나트륨금속	Na	溶融 溶融	○(100°C) ○(205°C)	○(100°C) ○(205°C)	○(100°C) ○(205°C)	○(100°C) ○(205°C)	×	×	×	×		×	×	×	×	×				
나프타	—		○	○		○	○	○(60°C)			○					×	△	×	×	
나프타(정제가솔린)	(石油系)		○(b.p.)	○(b.p.)	○(b.p.)	○(b.p.)	○	○(60°C)	×	○(26°C) ○(85°C) △	○	○	×	○(20°C)	○	○	×	△	×	○(70°C)
나프탈린	C ₁₀ H ₈		○	○	○	○		×	×	○	○	○	△(20°C)	○	○	×	×	×	△	
나프탈린·솔폰산	C ₁₀ H ₈ SO ₃ H ₂ O	○(20°C)	○(20°C)	○	○															
낙산	SC ₃ H ₇ COOH	×	○	○	○	○	×	○(22°C)	△	○	○	○	×	○(20°C)			×	×	×	
낙산폴리비닐	C ₄ HO ₂ (C ₂ H ₃) _n		○							○		○					○	○	×	
납	Pb	溶融 溶融 溶融	○(400°C) △(600°C) ×(900°C)	○(400°C) △(600°C) ×(900°C)		○	○													
뇌산수은(뇌통)	Hg(ONC) ₂ · 1/2H ₂ O		○						○		○					○				
니코틴	C ₁₀ H ₁₄ N ₂		○	○	○	○		○(60°C)	○	○		○	×		○	○	○	○	○	
니코린	C ₆ H ₅ NO ₂		○	○	○	○		○(60°C)	○	○		○			○	○	○	○	○	
니트로글리세린	C ₃ H ₅ ONO ₃		○	○	○	○	○				○				○	○	○		○	
니트로벤젠	C ₆ H ₅ NO ₂		○(b.p.)	○(b.p.)	○(b.p.)	○(b.p.)	×	×	×	○(70°C)	○(25°C)	○	×	○(20°C)		○	×	×	○	
니트로에텐	C ₂ H ₄ NO ₂		○(b.p.)	○(b.p.)	○(b.p.)	○(b.p.)				○		○				×	×	×	○	
당밀	C ₁₂ H ₂₂ O ₁₁	4~20	○	○	○	○		○	○(60°C)	○	○	○	○(60°C)	○	○	○	○(93°C)			
대구(어류)고기기름	—		○	○	○	○	○		○		○					○	○	×	○(24°C)	
데칼린	C ₁₀ H ₁₆		○(b.p.)	○(b.p.)	○(b.p.)	○(b.p.)				×	○(26°C)		×	○(20°C)			×	×	○(24°C)	
도금액			x													x				
구리	Cu			x					○	○	○(85°C)	○			○	○	×	×	○(88°C)	
금	Au			x					○	○	○(85°C)	○			○	○	x	○	○	
납	Pb			x					○	○	○(85°C)	○			○	○	x	○	○	
니켈	Ni			x					○	○	○(85°C)	○			○	○	x	○	○	
로듐	Rh			x					○	○	○(85°C)	○			○	○	x	○	○	
백금	Pt			x					○	○	○(85°C)	○			○	○	x	○	○	
아연	Zn			x					○	○	○(85°C)	○			○	○	x	○	○	
은	Ag			x					○	○	○(85°C)	○			○	○	x	○	○	
주석	Sn			x					○	○	○(85°C)	○			○	○	x	○	○	
카드뮴	Cd			x					○	○	○(85°C)	○			○	○	x	○	○	
크롬	Cr		x	x					○	○	○(25°C)	○			○		△	○	○	
크롬	Cr		x	x					○	△	△(85°C)	○					x(70°C)			
황동(놋쇠)			x						○	○	○(85°C)	○			○	○	x	○	○	
돼지기름(라아드)			○	○	○	○	○	○(60°C)	×	△		○				x		×	○	
동유	C ₁₀ ~C ₁₆ 탄화수소		○(b.p.)	○(b.p.)	○(b.p.)	○(b.p.)	○	○(60°C)	×	○(25°C) ○(85°C) △	○	○	○(23°C)	○	○	x	○	x	○(150°C) x(204°C)	
디메틸설포사이드	(CH ₃) ₂ SO	50 60		○(25°C) ○(95°C)																
디메틸아날린	C ₈ H ₁₁ N		○(b.p.)	○(b.p.)	○(b.p.)	○(b.p.)								○	○	x	×	×		
디메틸아민	(CH ₃) ₂ NH		○(b.p.)	○(b.p.)	○(b.p.)	○(b.p.)		×	22°C	△	△	○	○	○	○	x	×	×	○	

천세산업주식회사

액명	분자식	농도(%)	금속					플라스틱(합성수지)						내마모재		고무				
			STS-304	STS-316	Ti(티타늄)	하스테로이C	Aluminum	PVC 영화비닐	PE 폴리에틸렌	PP 폴리프로필렌	PCTFE 3불화에틸렌	Teflon 테프론	PMMA 아크릴	족연(글루)	세라믹	CR 네오프렌	NBR 부니-N	CSM 하이파렌	EPDM E.P.R	FPM 바이톤
디 부 틸 프 탈 펫	C ₆ H ₄ (COOC ₄ H ₉) ₂		○(b.p)	○(b.p)	○(b.p)	○(b.p)		×	○(100°C)	○(25°C)	○	△(20°C)			×	×	×	○	×	
디 아 세 톤 알 코 올	CH ₃ COCH ₂ C(OH)(CN ₃) ₂		○(b.p)	○(b.p)	○(b.p)	○(b.p)		×	×		○	×			×	×	○		×	
디 아 조 염	R-N=N-R			○				○	○		○				○		○		○	
디 에 밀 렌 글 리 풀	C ₄ H10O ₃		○(b.p)	○(b.p)	○(b.p)	○(b.p)		○(40°C)	○	○		○			○	○	○	○	○	
디 에 틸 렌 트 리 아 민	(CaH ₄) ₂ (NH ₂) ₃		○(b.p)	○(b.p)	○(b.p)	○(b.p)			△		○				○(b.p)			○	○	
디 에 틸 벤 헨	C ₈ H ₈		○(b.p)	○(b.p)	○(b.p)	○(b.p)	○		△	△		○				×	×	×	△(70°C)	
디 에 틸 세 론 르 프	—		○(b.p)	○(b.p)	○(b.p)	○(b.p)					○				○			△		
디 에 틸 아 민	(C ₃ H ₅) ₂ NH		○(b.p)	○(b.p)	○(b.p)	○(b.p)	○	×	△(20°C)	△(25°C)	○	×	△(20°C)	○	○	×	×	○	○	
디 에 틸 애 테 르	C ₂ H ₅ · O · C ₂ H ₂	100				○	○	×	(22°C)	△(20°C)	○	×	(20°C)	○	○	×	×		x	
디 이 소 부 틸 렌	C ₄ H ₉		○(b.p)	○(b.p)	○(b.p)	○(b.p)				○		○			○(b.p)	×	○(24°C)		○	○
디 이 소 부 틸 캐 톤	[(CH ₃) ₂ CHCH ₂] · CO		○(b.p)	○(b.p)	○(b.p)	○(b.p)	○				○				○(b.p)	×	△	○	×	(24°C)
디 젤 연 루	—		○(b.p)	○(b.p)	○(b.p)	○(b.p)					○				○(b.p)	○	○(70°C)	○	○	
디 크 품 산 칼 품	K ₂ Cr ₂ O ₇		○	○	○	○		○(60°C)	○	○		○			○	○	○	○	○	
디 클 로 로 벤 질	C ₅ H ₅ Cl ₃		○(b.p)	○(b.p)	○(b.p)	○(b.p)	○			○	○	○	○	×	○	○	×	×	×	(24°C)
(클 로 라 이 드)	C ₇ H ₅ Cl ₃									○	○	○	○	×	○	○	×	×	○	
디 클 로 로 에 탄	C ₃ H ₅ Cl ₂		○(b.p)	○(b.p)	○(b.p)	○(b.p)			×	△(20°C)	○	○	×	△(20°C)	○	○	×	×	○	△
디 클 로 로 에 틸 렌	C ₂ H ₄ Cl ₂		○(b.p)	○(b.p)	○(b.p)	○(b.p)				△		○			○	○	×	×	○	○(24°C)
디 페 닐	C ₆ H ₅ · C ₆ H ₅		○								○	○			○					
라 우 린 신	CH ₃ (CH ₂) ₁₀ · COOH			○					×	○		○			○					
락 카	—			○				○			○		×			×	×	—	×	(24°C)
레 몬 유	C ₁₀ H ₁₃	90		○			○				△		○			○	○	○	△	○
레 조 시 물	C ₆ H ₄ (OH) ₂			○(100°C)	○(100°C)		○(100°C)		×	×	○	○	×	(20°C)	○	○	×	×	×	○
리 놀 신	C ₁₆ H ₃₂ O ₂				○				×	○		○								○
리 조 물	—			○(20°C)	○(20°C)															
마 레 (인) 산	C ₄ H ₄ O ₄		○	○				○(60°C)	○	○	○	44% ○(25°C)	○		○	○	○	○	△	
마 요 네 즈	—			○(hot)	○(hot)		○(hot)	×		○		○				○				
망 간 영	—			○					○	○		○		○(60°C)		○	○	○	○	
액 주	—			○(70°C)	○(70°C)	○	○	×	○(60°C)	○	○(85°C)	○	○		○	○	○	○	○	
에 타 규 산 나 트 품	Na ₂ SiO ₃ · H ₂ O		○	○	○	○			○	○	○	○			○		○			
에 타 인 산 암 모 폼	(NH ₄) ₂ PO ₄		○	○	○	○			○(60°C)	○	○				○	○	○	○	○	
메 틸 아 민	CH ₃ NH ₂		○(b.p)	○(b.p)	○(b.p)	○(b.p)	○			○	○		○	○(20°C)		○	○	×	○	
에 틸 알 데 히 드	HCHO	40	○(b.p)	○(b.p)											○	○				
에 틸 알 코 콜 (메 타 놀)	CH ₃ OH	dil conc.	○(b.p)	○(b.p)	○(b.p)	○(b.p)	○	○(60°C)	○	○(85°C)	○(60°C)	○(121°C)	×	×	○	○	△	○(93°C)	○(24°C)	
메 틸 에 틸 케 품	C ₂ H ₅ · COCH ₃		○(b.p)	○(b.p)	○(b.p)	○(b.p)	○	×	(22°C)	×	△(70°C)		○	×	○	○	×	×	○	×
에 틸 이 소부 틸 케 품 (MIBK)	CH ₃ COCH ₂ · CH(CH ₂) ₂		○(b.p)	○(b.p)	○(b.p)	○(b.p)	○			×	○(26°C)	△ ×(85°C)			○	○	×	×	○	×
에 틸 클로로 포 품	CH ₃ CHCl ₂		○	○						△	○	○	×			×	×	×	×	○
면 실 유	—		○	○	○	○		○(60°C)	○	○		○			○	○	△	○(70°C)	○(150°C)	
명 빈	—			×		○	×		○	○(85°C)		○			○	○	○	○(93°C)	○(100°C)	
크롬명반	Cr ₂ (SO ₄) ₃ · K ₂ SO ₄			△				○(60°C)	○	○(85°C)		○			○	○	○	○	○	
황산알루미늄 · 칼륨명반	Al ₂ (SO ₄) ₃ · K ₂ SO ₄	dil conc.	×	×	×	△		○(60°C)	○	○(85°C)	○	○	○(20°C)		○	○	○	○	○	
모 노 에 탄 올 아 민	NH ₂ C ₂ H ₄ OH			○(b.p)	○(b.p)	○(b.p)	○(b.p)		○	○		○			○		○	○	○	
무 수 초 신	(CH ₃ · CO) ₂ O		○	○	○(b.p)	○(b.p)		×	×	○	○				○	○(b.p)	×	○	○(79°C)	
무 수 황 신	SO ₃														○	○(b.p)				

천세산업주식회사

액명	분자식	농도(%)	금속					플라스틱(합성수지)						내마모재		고무					
			STS-304	STS-316	Ti(티타늄)	하스테로이C	Aluminum	PVC 영화비닐	PE 폴리에틸렌	PP 폴리프로필렌	PCTFE 3불화에틸렌	Teflon 테프론	PMMA 아크릴	족연(글루)	세라믹	CR 네오프렌	NBR 부니-N	CSM 하이파렌	EPDM E.P.R	FPM 바이톤	
물식자신	-	-	○(b.p)	○(b.p)		○		○		○	○	○		○							
바니쉬	-	-	○	○		○		○(60°C)						○	○	○	×				
벤조알데히드	C ₆ H ₅ CHO	-	○	○	○	○	△	×	(22°C)	×	○(26°C) △(85°C)	△(25°C)	○	×	(20°C)	○	○	×	×		
부탄올	C ₄ H ₉ OH	-	○	○	○	○	○	○(60°C)	△	○(85°C)	○(25°C)	○(121°C)	×	(20°C)	○	○	○	○	○		
부틸렌	C ₄ H ₈	-	○	○	○	○		○(22°C)	△	△		○	×						○		
불화가스	F ₂	-	×	×	×	○		×	×	×		×									
불화	CuF	-	-	-	-	-		○(60°C)	○	○		○	○(60°C)			○	○	○	○		
불화마그네슘	MgF ₂	-	-	-	-	-		○(60°C)	○	○		○	○(60°C)			○	○	○	○		
불화소다	NaF	-	△	△		○	○	○(60°C)	○	○	○	○	○(60°C)		○	○	○	○	○		
불화수소(증기)	HF	vapor	○(100°C)	○(100°C)				×						○		○	○	○	○	○	
불화수소산(불산)	HF	dil	×	×	×	○(30°C)	×	×	(24°C)	○(24°C)	△(25°C)	○	○	○(20°C)	○(b.p)	×	×	×	○(149°C)	48%	
		40						×		△(26°C)	50%↓	○(60°C)								○(24°C)	
		conc.	×	×	×	△(30°C)	×	×	○(30°C)	○	○	○		○	×	×	×	△(70°C)	○		
		60						△(24°C)	○												
		60								×											
		>60						×	△		○					×	×	△	×	△(100°C)	
불화알루미늄	AlF ₃	-	-	-	○	△		○(60°C)		○(85°C)	○	○	○(60°C)		○	○	○	○	○	○	
불화암모늄	NH ₄ F	-	△	△		×	×	○(60°C)	○	○		○	○(60°C)		○	○	○	○	○	○	
불화칼륨	KF	-	-	-	○			○(60°C)	○	○(85°C)	○	○	○(60°C)		○	○	○	○	○	○	
불화소다(나트륨)	NaBF ₄	-	-	-	-		△			○		○				○	×	○	○	○	
불화수소산	HBF ₄	-	-	-	-		×		○	○(85°C)		○				○	○	○	○	○	
봉사	Na ₂ B ₄ O ₇ · H ₂ O	-	○(溶融)	○(溶融)	○	○(溶融)		○	○	○	○	○	○(60°C)		○	○		○(93°C)	○	○	
봉신	H ₃ BO ₄	-	△	△	○	○		○(60°C)	○	○(70°C)	○	○			○	○	○	○(73°C)	○	○(93°C)	
봉산소다	Na ₂ BO ₂ · 5H ₂ O	-	○	○	○	○	△	○(60°C)	○	○		○	○(60°C)		○	○	○	○(93°C)	○	○	
봉산칼륨	KBO ₂ · 4H ₂ O	-	-	-	-				○	○		○	○(60°C)		○	○	○	○	○	○	
브롬소가스	Br ₂ gas	dry	×	(24°C)	×	(24°C)		○	×			○			×	○				○	
		wet	×	×	○	○	×	×	(22°C)	×	×	○(25°C)	○		×	○	×	×	×	△	
		water	×	×		○	×		×	○(26°C)	○	○			×	○	×	×	×	○(70°C)	
브롬소산소다	NaBrO	-	-	-	-				○	○		○	○			△	×	○	○	○	
브롬소산칼륨	KBrO ₃	-	△	○	△	△		○(60°C)	○	○	○	○			○	○	○	○	○	○	
브롬화메틸	CH ₃ Br	-	-	-	○					×		○	×		○	×	×	△			
브롬화소다(나트륨)	NaBr · 2H ₂ O	-	△	△	×	△		○(60°C)	○	○		○	○(60°C)		○	○	○	○	○	○	
브롬화수소산	HBrO ₃	50	×	(24°C)	×	(24°C)	○	△	20%	△	○(70°C)	○(25°C)	○(25°C)	40%		○	○	×	○	○	△
브롬화암모늄	NH ₄ Br	-	△	△							○	○	○		○	○				○	
브롬화칼륨	KBr	-	△	△	○	○		○(60°C)	○	○(85°C)	○	○	○		○	○	○	○	○	○	
비누액	-	○	○	○	○	○		○(60°C)	△	○	○	○	○		○	○	○	○(93°C)	○	○	
비신	HAsO ₃	-	△	△	×	△		○(60°C)	△	○	○	○	○		○	○	○	○	○	○	
빙초선	CH ₃ COOH	>98%	△(100°C)	△(100°C)						×	○						○(24°C)	×	△	×	
사과선	C ₄ H ₆ O ₅	-	○	○		○	△		○	○(85°C)	○	○	○(60°C)		○	○	○			×	
사봉산소다	Na ₂ B ₄ O ₇	20	-	-	-	-															
사영화탄소	CCl ₄	-	○	○	○(b.p.)	○(b.p.)	×	△(20°C)	×	(20°C)	×	○	○	×	○	○	×	×	×	○	
사영화티탄	TiCl ₄	-	○	○	○(b.p.)	○(b.p.)		△		○	○	○			○	○	△(24°C)	×	△	○	
사이클로헥사논	C ₆ H ₁₀ O	-	○(b.p.)	○(b.p.)	○(b.p.)	○(b.p.)		×	(22°C)	×	○(25°C)	○(25°C)	○	×	(20°C)	○	○	×	×	×	
사이클로헥사놀	C ₆ H ₁₁ OH	-	○(b.p.)	○(b.p.)	○(b.p.)	○(b.p.)		×	○(22°C)	×	○(25°C)	○(25°C)	○	×	(20°C)	○	○	×	○	○	

천세산업주식회사

액명	분자식	농도(%)	금속					플라스틱(합성수지)						내마모재		고무				
			STS-304	STS-316	Ti(티타늄)	하스테로이C	Aluminum	PVC 영화비닐	PE 폴리에틸렌	PP 폴리프로필렌	PCTFE 3불화에틸렌	Teflon 테프론	PMMA 아크릴	족연(글루)	세라믹	CR 네오프렌	NBR 부나-N	CSM 하이파렌	EPDM E.P.R	FPM 바이톤
사 이 클로 헥신	C ₆ H ₁₂		○(b.p)	○(b.p)	○(b.p)	○(b.p)	○	×	×			○	×	(20°C)	○	○	×	○	×	○(24°C)
사 진 정 착 액	-		×	×	○	○	△	○(60°C)		○		○	○	○	○		○	○	○	×
사 진 현상 액	-		○(20°C)	○		○	△	○(60°C)	○	○		○	○	○	○	○	○	○	○	×
사 탕 무 우 당 액	C ₁₂ H ₂₂ O ₁₁	4~20	○	○	○	○		○	○	○	○	○	○(60°C)	○	○	○	○	○	○	○
산 소	O ₂		○	○	○	○		○	○	○		○		○	○	○	○	○	○	○
산화 규소 (실리카) (무수 규산)	SiO ₂		○	○	○	○	○	○	○	○		○		○	○	○	○	○	○	○
산화 안티모니	Sb ₂ O ₃								○	○	○		○	○	○	○				○
산화 에틸렌	C ₂ H ₄ O																			
산화 우라늄	UO ₂		○													○	○	○(93°C)	○	○
산화 칼슘	CaO	lime														○	○	○	○	○
살리실산	C ₇ H ₆ O ₃		○(20°C)	○(20°C)		△		○						○	○					
살리실산 소다 (나트륨)	NaC ₇ H ₅ O ₃		○(20°C)	○(20°C)			△													
살리실산 애밀	C ₆ H ₄ (OH)COOCH ₃			○									○	×		×	×	×	×	○
삼불화봉소	BF ₃		○	○						×	○	○		○	○	○	○	○	○	○
삼산화유황 (무수 유산)	SO ₃		○	○				○				○				○	×	×	×	○
삼염화붕소	BCl ₃			○						×	○		○						○	○
삼염화안티모니	SbCl ₃			×				×	○	○	○	○	○			○	△	△	△	△
삼염화에틸렌 (트리클로レン)	C ₂ HCl ₃	100	○(b.p)	○(b.p)	○(b.p)	○(b.p)	○(b.p)	×	×	×	△	△	○		×	○	○	×	×	○(24°C)
삼염화인	PCl ₃		○	○	○			×					○		○	○	×	×	○	○
삼염화초산	C ₂ HCl ₃ O ₂	10		×					×	×	○		○		×	○	×	×	○	×
석고	CaSO ₄		○	○	○	△	○		○	○	○	○	○		○	○	△	○	○	○
석유	-		○(b.p)	○(b.p)	○(b.p)	○(b.p)	○(b.p)	○	○	×	○	○	○(25°C)	○		○	○	○	○	
석회현탁액	-		슬러리	○				△		○	○		○	○		○	○	○(73°C)	○(93°C)	
세라믹	-		슬러리	○				△		○	○		○			○	○	○	○	
세파신산티오에틸	-		○	○	○	○	○			×	△		○	△(20°C)		○	×	×	○	△
소석회 (수산화칼슘)	Ca(OH) ₂						△				○	○			○	○	○	○	○	○
송진유	-		○	○		○					○	○				○		○	○	○
수력용유	-		○								○	○				○	○	○	○	○
수신	(COOH) ₂ · 2H ₂ O	dil dil conc. conc.	○ × ○×	○△(60°C) ×	○(21°C) ×	×	○ ○(21°C) ×	○ ○(60°C)	○(29°C) ○(30°C)	dil○ 15% ○(100°C)	飽和 ○(121°C) ○	○(20°C) 飽和		○	○	○(73°C)	○	△	○	
수산소다 (나트륨)	Na(COO) ₂			○						○	○		○	○(60°C)		○	○	○	○	○
수산암모늄	(NH ₄) ₂ C ₂ O ₄ · H ₂ O				○			×		○	○		○	○(60°C)		○	○	○	○	
수산칼륨	K ₂ (COO) ₂		○(b.p)	○(b.p)										○(60°C)		○				
수산화리튬	LiOH		○	○	○	○				○	○		○	○(60°C)		○	○	○	○(93°C)	
수산화마그네슘	Mg(OH) ₂		○	○	○	○		×	○(b.p)	○	○	○	○	○(60°C)		○	○	○	○	
수산화바륨	Ba(OH) ₂		○	○	○	○		×	○(b.p)	○	○(85°C)	○	○	○(60°C)		○	○	○	○	
수산화알루미늄	Al(OH) ₃		○	○	○	○		○	○(b.p)		○	○	○	○(60°C)		○		○(93°C)		
수산화제1철	Fe(OH) ₂			×					○	○	○		○	○(60°C)		○			○	
수산화제2철	Fe(OH) ₃			○					○	○	○		○	○(60°C)		○		○	○	
수산화칼리움	KOH																			
수산화칼슘	Ca(OH) ₂		○	○	○	○	×	○(b.p)	○	○	○	○	○(60°C)		○	○	○	○	○(93°C)	
수소가스	H ₂		○	○		○		○	○(b.p)		○	○	○			○	○	○	○	
수증	Hg		○(50°C)	○(50°C)	○	○	△	○(b.p)	○	○		○	○		○	○	○	○	○	

천세산업주식회사

액명	분자식	농도(%)	금속					플라스틱(합성수지)						내마모재		고무					
			STS-304	STS-316	Ti(티타늄)	하스테로이C	Aluminum	PVC 영화비닐	PE 폴리에틸렌	PP 폴리프로필렌	PCTFE 3불화에틸렌	Teflon 테프론	PMMA 아크릴	족연(글루)	세라믹	CR 네오프렌	NBR 부니-N	CSM 하이파렌	EPDM E.P.R	FPM 바이톤	
솔	—		○(70°C)	○(70°C)									○								
스 테 아 린 산	C ₁₇ H ₃₅ · COOH		○	○	○	○			○	○	○(85°C)	○	○		○	○	△	△(70°C)	△	○	
시 안 (청) 화 소 다	NaCN		○	○	○	×	×	○(60°C)	○	○	○	○	○(60°C)		○	○	○	○(93°C)	○	○	
시 안 (청) 화 아 연	Zn(CN) ₂		○(20°C)	○(20°C)	○	○	×	○	○	○		○	○		○	○	○	○	○	○	
시 안 (청) 화 칼 풀	KCN		○	○	○	○	×	○(60°C)	○	○		○	○		○	○	○	○	○	○	
시 안 (청) 화 은	AgCN						×	○(60°C)		○		○			○	○				○	
시 안 암 산	HCN						×														
시 안 화 동	Cu(CN) ₂	飽和	○ ○(b.p)	○ ○(b.p)		○	×	○(60°C)	○	○	○	○	○(60°C)	○	○	○	○	○	○	○	
시 안 화 수 소 산	HCN	dilute ngas cone.	×	×				○					×	○	○	△	○	○			
(청 화 수 소 산)			○	○		○		○			○(85°C)	○	○								
(청 산)(시 안 산)																					
식 물 유	—		○(高溫)	○(高溫)																	
식 초	CH ₃ COOH		○	○	○	○	×	○(b.p)	○	○	○	○	○(20°C)	○	○	○	×	○	○	○	
아 달 린	C ₆ H ₅ NH ₂	100	○	○(100°C)	○	○	×	×	(22°C)	×	(24°C)	○(23°C)	○(65°C)	○(24°C)	×	○	○	×	×	△	○(24°C)
아 디 프 신	COOH(CH ₂) ₄ COOH		△	△	○	○		○(60°C)	○	○	○	○			○	○			△	○	
아 질 알 코 올	CH ₂ :CHCH ₂ OH		○(b.p)	○(b.p)	○(b.p)	○	△	○(60°C)	○	○		○(121°C)	×	(20°C)	○	○	○	△	○	×	○
아 마 인 유	C ₅ H ₁₁ OH		○	○	○	○				×	○	○(25°C)	○			○	○	△	○	○	○(121°C)
아 민 름	R-NH ₂		○	○		○					○	○	○		○	○				x	
아 일 알 코 올	C ₅ H ₁₁ OH		○(b.p)	○(b.p)	○(b.p)	○(b.p)		○(60°C)	○(60°C)	○(85°C)		○(b.p)	×	(20°C)	○(b.p)	○(b.p)	○	○	○(93°C)	○	○(24°C)
아 세 톤 (DMK)	CH ₃ COCH ₃		○(b.p)	○(b.p)	○(b.p)	○(b.p)	○	×	(22°C)	×	△	○	○	×	○	○	△(24°C)	×	△	○	
아 세 트 산	CH ₃ COOH						○					○			○	○	○	○			×
아 세 트 아 미 드	C ₈ H ₉ NO ₃			○(b.p)	○(b.p)	○(b.p)					○						×	×	○	○	○(100°C)
아 세 트 알 데 하 드	CH ₃ CHO		○(b.p)	○(b.p)	○(b.p)	○(b.p)	△	×	(22°C)	△	○	○	○	×	○	○	×	○	○	×	○
아 세 틸 랜	CH ₂ H ₂		○	○		○	○		○			○			○	○			○		
아 염 소 산 소 다 (나 트 름)	NaClO ₂		×	×	○(100°C) 30%	○	10%	×	○		○(25°C) 40%	○		○(100°C) 100%	○	×	×	○	○	○	○
아 유 산	H ₂ SO ₃			×	×	○	△		○(60°C)		○	75% ○(25°C)	○		○	○	×	×	○(70°C)	×	○
아 질 산	NHO ₂		○	○				×			○	○	○		○	○	×	○	○		○
아 질 산 소 다 (나 트 름)	NaNO ₂		○	○	○ 40%			×	○(60°C)	○	○	40% ○(25°C)	○	○(60°C)	○	○	○	○	○	○	○
아 취 산 소 다	NaBrO ₂		△	△	×	×			○	○	○	○	○			○	○	△	○	○	
아 크 릴 로 니 트 릴	CH ₂ :CHCN		○(b.p)	○(b.p)	○(b.p)	○(b.p)				×	○(70°C)	△(25°C)	○	×	(20°C)	○	○	×	×	○	×
아 질 산 카 리	KNH ₂		△	△	○	△									○	○					
아 크 릴 산 애 릴	CH ₃ :CHCO ₂ CH ₃		○(b.p)	○(b.p)	○(b.p)	○(b.p)				○	○(20°C)	○	×				×	×	×	×	
아 크 릴 산 애 릴	CH ₂ :CHCO ₂ C ₂ H ₅		○(b.p)	○(b.p)	○(b.p)	○(b.p)				○	○		×	(20°C)			×	×	×	×	
아 크 릴 산 애 릴 학 실	C ₁₁ H ₂₁ O ₂									○	○	○	×				×	×	×	×	
아 황 산 가 스	SO ₂	dry wet	○ ×	○ ○	○ △	○ ○		○(60°C) ○(60°C)			○(40°C) ○(25°C)	○(121°C) ○(200°C)			○(200°C) ○(200°C)	○(200°C) ○(200°C)	○(30°C)1% ○(30°C)1%	△ △(65°C)	○(70°C) x		△
아 활 산 소 다 (나 트 름)	Na ₂ SO ₃ · 7H ₂ O			○(b.p)	○(b.p)	○(b.p)	○	○	○(30°C)	○	○	○	○	○(60°C)	○	○	△	○	○	○	○
아 활 산 수 소 나 트 름 (소 다)	NaHSO ₃			○(20°C) ○(100°C)	○(20°C) ○(100°C)	○(b.p)	○(b.p)	△	○(30°C)	○	○	○	○(b.p)	○(60°C)	○(b.p)	○(b.p)	○	○	○	○	○
아 활 산 수 소 일 모 능	NH ₄ HSO ₃			○(b.p)	○(b.p)	○(b.p)	○(b.p)		○(30°C)	○	○	○(b.p)	○(60°C)	○(60°C)	○(b.p)	○(b.p)	△	×	○	×	○
아 활 산 수 소 칼 승	Ca(HSO ₃) ₂			○(b.p)	○(b.p)	○(b.p)	○(b.p)		○(30°C)	○	○	○(b.p)	○(60°C)	○(60°C)	○(b.p)	○(b.p)	○	○	○	○	○
아 활 산 암 모 능	(NH ₄) ₂ SO ₃			○(b.p)	○(b.p)	○(b.p)	○(b.p)		○(30°C)	○	○	○(b.p)	○(60°C)	○(60°C)	○(b.p)	○(b.p)	○	△	○	○	○
아 활 산 칼 풀	K ₂ SO ₃			○(b.p)	○(b.p)	○(b.p)	○(b.p)		○(30°C)			○(b.p)	○(60°C)	○(60°C)	○(b.p)	○(b.p)	△	△	△		

천세산업주식회사

액명	분자식	농도(%)	금속					플라스틱(합성수지)						내마모재		고무					
			STS-304	STS-316	Ti(티타늄)	하스테로이C	Aluminum	PVC 영화비닐	PE 폴리에틸렌	PP 폴리프로필렌	PCTFE 3불화에틸렌	Teflon 테프론	PMMA 아크릴	족연(글루)	세라믹	CR 네오프렌	NBR 부니-N	CSM 하이파렌	EPDM E.P.R	FPM 바이톤	
안식향신	C ₆ H ₅ COOH			○(100°C)		○(100°C)		○(24°C) ○(40°C) ○(66°C)	○(24°C) ○(40°C) ○(70°C)	○ ○(40°C) ○(60°C)				○	○(100°C)	○(73°C)					
안식향산소다 (나트륨)	C ₆ H ₅ COONa		○	○	○	○		○(60°C)	○	○		○			○	×	○	○	○		
안트라퀴논	C ₁₆ H ₁₄ O ₂			○				○(22°C)	×	△		○						△			
암모늄동	Cu(NH ₄) ₂							○	○		○				○		○	○			
암모니아	NH ₃	gaswet gaswet	○(20°C) ○(100°C)	○(20°C) ○(316°C)	○(40°C)	○(40°C)	×	all ○(60°C) ○(60°C)	○(60°C)	○(60°C)	○(25°C) 10%	○	× (20°C)	○	○	○(24°C)	×	△	×		
암모니아수	NH ₄ OH	20 30 100	○(100°C)	○(100°C)	○(30°C)	○(100°C)	×	○ ○(60°C)	○ ○(60°C)	○ ○(20°C) 28% ○(80°C) ○(160°C)	○ ○(121°C)	○(60°C) 10% ○(20°C) 30%		○	○	○(65°C) ○(24°C)	○(65°C)	○ ○	○(24°C) ○(24°C)		
액화프로필렌	C ₃ H ₆ (-46°C)		○	○	○	○	○				○	×			×		×	○	×		
에탄올 (에틸알코올)	C ₂ H ₅ OH		○(20~100°C) 100%	○(20~100°C) 100%	○ 100%	○ 100%	×	○(60°C)	○(24°C) 10%↓ × (52°C)	10% ○(25°C) ○(85°C)	○(25°C) 10%↑ ○(121°C) 100%	○(25°C) 95%	×	○	○(b.p) 10~100% ○	○(24°C) ○(70°C)	○(b.p)	○(93°C)	○ 10~100% ○(24°C) ○(93°C)		
에테르	(C ₂ H ₅) ₂ O		○	○	○	△	○	○	○	○	○			○	○	○			○		
에틸렌글리콜	(CH ₂ OH) ₂		○	○			○	○(60°C)	○	○(85°C)	○	○	○(20°C)		○	○	○(60°C)	○(40°C)	○(93°C)	○ ○(121°C)	
에틸렌옥사이드 (酸化에틸렌)	(CH ₂) ₂ O		○(b.p)	○(b.p)	○(b.p)	○(b.p)	○	×	○(22°C)				△(20°C)		○(b.p)	×	×	×	×	×	
연료유	—		○	○	○	○		○	×	○	○	○			○	○	○	△(70°C)	×	○	
염료	—	中性 酸性 鹽基性	○(b.p) ○(b.p) ○(b.p) ○(b.p)	○(b.p) ○(b.p) ○(b.p) ○(b.p)																	
염수산	HCl	dil	×	×	○	○	×	○(65°C)	○(60°C)	○(20°C) ○(70°C) ○(100°C)	○ ○(100°C)	○(24°C)	○(60°C) 30%	○(b.p)	○	○(72°C)	×	○	○ ○(70°C)		
		comc	×	×	×	○	×	○(65°C)	○(65°C)	○(20°C) 37% ○(100°C)	○(24°C)	○(20°C)	○(b.p)	○(b.p)	×	×			×	×	
					×	○(b.p)														×	110°C
염소가스	Cl ₂	dry<0.01% H ₂ O	△	△	×	○	×	×	○(22°C)			△(50°C)	○(121°C)		○	○	×				○(100°C)
		wet	×	(20°C) × (100°C)	×	×	○ ×	×	×	○(22°C)			△(50°C)	○		×	○	×			
		water	×	(20°C)	×	○	○			×	○	△(50°C)	○	○(20°C)10%	○	○	×	×	△	×	○
염소산	HClO ₃		×	×					○(20°C)		○	○									
염소산소다	NaClO ₃		×	×	○	○	○		○(60°C)	○	○		○(20°C)		○	○	×	○	○(93°C)	○ ○	
염소산칼슘	KClO ₃	飽和	○ ○(100°C)	○ ○(100°C)	○	○			○	○	○	○	○(120°C)		○	○	○	○	○	○	
염소산칼슘	Ca(ClO ₃) ₂		△	△	△	△		○(60°C)	○	○	○	○			○	○	○	○	○	○	
염화나트륨	NaCl		×	×	○	○	△		○	○	○(85°C)	○(160°C)	○(121°C)	○(60°C)		○	○	○	○(105°C)	○ ○	
염화니켈	NiCl ₂		×	×	○(70°C)	○	○		○(65°C)	○	○	○	○	○(60°C)		○	○	○(80°C)	○(80°C)	○ ○	
염화철	CuCl ₂		×	×	○	○	○		○(60°C)	○	○	○	○	○(60°C)		○	○	○(73°C)	○ ○		
염화라듐	RaCl ₂			×						○	○		○				○	×	○	○	
염화라우릴	CH ₃ (CH ₂) ₁₀ CH ₂ Cl				○					×	○		○								
염화로듐	RhCl ₃				○						○		○								
염화리튬	LiCl				○						○		○								
염화마그네슘	MgCl ₂		△	△	○	△	×	○	○	○	○	○	○(60°C)		○	○	○(73°C)	○(104°C)	○ ○		

천세산업주식회사

액명	분자식	농도(%)	금속					플라스틱(합성수지)						내마모재		고무				
			STS-304	STS-316	Ti(티타늄)	하스테로이C	Aluminum	PVC 영화비닐	PE 폴리에틸렌	PP 폴리프로필렌	PCTFE 3불화에틸렌	Teflon 테프론	PMMA 아크릴	족연(글루)	세라믹	CR 네오프렌	NBR 부나-N	CSM 하이파렌	EPDM E.P.R	FPM 바이톤
염화망간	MnCl ₂		○(b.p)	○(b.p)	○	○		○	○	○	○	○	○(60°C)	○	○	○	○	○	○	
염화메틸	CH ₂ Cl		○	○	○	○	×	×	(22°C)	△	○	○	×	○	○	×	×	×	△(38°C)	
염화메틸렌	CH ₂ Cl ₂		○(b.p)	○(b.p)	○	○	○	×	(22°C)	×	○	○	×	○	○	×	×	×	△	
염화바륨	BaCl ₂		○	○	○	○	×	○(60°C)	○	○(85°C)	○	○	○(60°C)	○	○	○	○	○	○	
염화벤젠	C ₆ H ₅ Cl		○(b.p)	○(b.p)	○	○		×	×	×	○	○	×	○	○	×	×	×	×	
염화벤조일	C ₆ H ₅ COCl		△	△		△				○				○					△	
염화벤조질	C ₆ H ₅ CH ₂ Cl		○	○	○	○				○	○	○	×	○	○	×	×	×	△	
염화부단디엔	C ₄ H ₈ Cl		○	○	○	○				×	○	○	×					○	○	
염화브롬화메틸렌	CH ₂ ClBr		○							×	×	○	×	○	○	×	×	×	△	
염화수소가스	HCl	dry	○(20°C) △(100°C)	○(25°C) △(100°C)			○(45°C)	×			○(100°C)			○	○					
		wet		×						○	○	○(100°C)	○						○	
염화아닐린	C ₆ H ₅ NHCl	5	×	×					×	(22°C)										
염화아민	C ₅ H ₁₁ Cl			○			×		×	(22°C)	×	×	○	×	○	○	×	○	○	
염화아세틸	CH ₃ COCl		×	○						×	○	○	○		○			○	○	
염화아연	ZnCl ₂		○	○	○	○	×	○(80°C)	○	○(85°C)		○		○	○	○	○	○	○	
염화안티몬	SbCl ₃		×	×	○	○		○	○	○				○	○	○	○	○		
염화알루미늄	AlCl ₃		△	△	○	○	○(30°C)	×	○(65°C)	○(65°C)	○(65°C)	○	○	×	○	○(100°C)	○(65°C)	○	○	
염화암모늄	NH ₄ Cl		△50°C	○(b.p)	○(100°C)	△(80°C)	×	○(65°C)	○	○	27% ○(25°C)	○	○(20°C)	○	○(100°C)	○(35°C)	○	○	○	
염화에틸	C ₂ H ₅ Cl		○(b.p)	○(b.p)	○(b.p)	○(b.p)	△	×	(22°C)	○	○	○	×	○	○	△	×	△	○	
염화에틸렌	C ₂ H ₄ Cl ₂		○(b.p)	○(b.p)	○(b.p)	○(b.p)	×	×	(22°C)	○	△	○(25°C)	○	×	○	○	×	○	△(80°C)	
염화우라늄	UCl ₄			×					○	○						○	○	○	○	
염화유황	S ₂ Cl ₂	dry wet		○			×						○(60°C)	○	○					
염화은	AgCl		×	×	○	○			○	○	○	○	○(60°C)	○	○	○	○	○	○	
염화제1수은	Hg ₂ Cl ₂			×				×	○(60°C)	○	○		○(60°C)	○		○	○	○	○	
염화제1주석	SnCl ₂		×	×	○	○	×	×	○	○	○	○	○(60°C)	○	○	○	○	○	○	
염화제1철	FeCl ₂		×	×	○	○	×	×	○(60°C)	○	○	○	○(20°C)	○	○	○	○	○	○	
염화제2석	SnCl ₄		×	×	○	○	○		○	○	○	○(25°C)	○	○(60°C)	○	○	○	△(93°C)	○	○
염화제2수은	HgCl ₂		×	×	○	○	△		○(60°C)	○	○(85°C)	○	○(60°C)	○	○	○	○	△	○	
염화제2철	FeCl ₃		×	×	○	○	○(15°C)	×	○(60°C)	○	△(85°C)	○	○(60°C)	○	○	○	○(100°C)	○(93°C)	○	○
염화초신	C ₂ HClO ₂		×	×	○	○	○		○	×	×	○	○	×	○	○	×	○	△	
염화칼륨	KCl	飽和	○(100°C) 30%	○(100°C) 30%	○	○	×	○(60°C)	○(55°C)	○	○	○	○	○	○	○(73°C)	○	○	○	
염화칼슘	CaCl ₂		△	△	○	○	○(110°C)	△	○(65°C)	○(40°C)	○(85°C)	○(25°C)	○(121°C)	○(20°C)	○	○(75°C)	○(45°C)	○(75°C)	○	○
염화프로필렌	C ₃ H ₅ Cl ₂		○	○	○	○			×	(22°C)		×								
오산화인(無水磷酸)	P ₂ O ₅	dryor wet	○(20°C)	○(20°C)	○	○	△	○	○	○			○(60°C)	○	○	○	○	○	○	
온	O ₃		○	○					○(20°C)			○	○		○	○	○	○	○	
온수수기	—		○	○	○	○			○	○	○	○	○		○	○	×	×	△(70°C)	
옥토포름	CH ₃ I ₃		×	○				△		×	×	○			○	×	×	×	×	
풀레인산	—		○(20°C) ○(200°C)	○(20°C)	○	○	○		○	○(24°C) △(66°C)	○	○(25°C)	○(24°C) ○(121°C)		○	△	○	△	○	
풀리브유	C ₁₈ H ₃₂ O ₂ C ₁₆ H ₃₂ O ₂	83.5 9.4	○	○	○	○	○		×	○(22°C) ○(70°C)	○	○	○(20°C)	○	○	×	○	○	○(24°C)	
왕수	HCl+HNO ₃	3:1		×	○(30°C) ×(70°C)			×		×	○(25°C) ×(85°C)	○(25°C)	○	×	×	×	×	△	×	
요신	C ₅ H ₄ N ₄		○(20°C)	○(20°C)																
요소	CO(NH ₂) ₂			○					○(60°C)	○	○	○	○		○	○	×	○(93°C)	○	×
요오드가스	I ₂	dry wet	○(20°C) ×	○(20°C) ×		×	×	×	×	(22°C)	×		○	○	×				○	
요오드화소다	NaI			○				×		○	○		○	○(60°C)	○	○	○	○	○	

천세산업주식회사

액명	분자식	농도(%)	금속					플라스틱(합성수지)						내마모재		고무					
			STS-304	STS-316	Ti(티타늄)	하스테로이C	Aluminum	PVC 영화비닐	PE 폴리에틸렌	PP 폴리프로필렌	PCTFE 3불화에틸렌	Teflon 테프론	PMMA 아크릴	족연(글루)	세라믹	CR 네오프렌	NBR 부니-N	CSM 하이파렌	EPDM E.P.R	FPM 바이톤	
요오드화수소신	HI			x			x		x	x	○	○		○	x	x	x	x	○		
요오드화칼륨	KI	conc.	△(b.p)	△(b.p)	○	△	x						○(60°C)	○	○					○	
우란황 (우란산소다)	Na ₂ UO ₄			○					○	○		○			○	○	○	○	○		
우유	-			○(hot)	○(hot)		○(hot)	○		○	○		○			○	○	○			
원유	-			○(b.p)	○(b.p)	○(b.p)	○(b.p)	○		○	○		○		○	x	△	x	x	○	
위스키	C ₂ H ₅ OH			○	○		○	x	○(60°C)	○(85°C)	○		○		○	○	×	○	○	○	
유산신 (젖산)	C ₃ H ₆ O ₃			○(b.p)	○(b.p)	○(b.p)	○(b.p)	△	○(60°C)	○	○	○	○		○	○	○(70°C)	○	△	△	
유황	S	溶融	○(130°C)	○	○(200°C)	○		○(60°C)						○	○	○				○(121°C)	
윤활유	-			○	○	○	○	○					○			x	△	△(70°C)	x	○	
이소옥tan	CH ₃ C(CH ₃) ₂			○(b.p)	○(b.p)	○(b.p)	○(b.p)				○	○(b.p)	○(20°C)	○	○(b.p)	○(30°C)	○(b.p)	○(60°C)	○	○(24°C)	
이소프로판올 (이소프로필알코올)	(CH ₃) ₂ CHOH(CH ₃) ₂			○(b.p)	○(b.p)	○(b.p)	○(b.p)		○(40°C)	○	○		○(121°C)	x(20°C) ○(20°C)	○	○(b.p)	○(24°C)	○	○	○(70°C)	
이소프로필에틸	(CH ₃) ₂ CHOH(CH ₃) ₂			○(b.p)	○(b.p)	○(b.p)	○(b.p)			○	○	○(b.p)	x		○(b.p)	x	×	×	△	x	
이염화탄소	CCl ₄	100		○	○(30°C)	○	○														
이염화티탄	TiCl ₄			○	○	○	○			○	○		○		○	○	○	○	○	○	
이염화프로필렌	C ₃ H ₅ Cl ₂			○	○	○	○				x	○(25°C)	○		○	x	×	×	○	○	
이취화에틸렌	CH ₂ Br ₂				○					x			○	x(20°C)	○		○	○(24°C)			
이황화칼슘	Ca(HS) ₂			x	x	○			○	x	x	○	○		○	x	x	x	○	○	
이황화탄소	CS ₂			○(b.p)	○(b.p)	○(b.p)	○(b.p)		x(22°C)	x	x	○(25°C)	○	○(20°C)	○	○	○	×	×	○(24°C)	
인산	H ₃ PO ₄	dhl	○(b.p)	○(b.p)	○	○(b.p)	x x	○	○(60°C)	○(60°C)	○	○(20°C)	○(80°C)	○	○(65°C) ○(93°C) ○(93°C)	x	○(93°C)	○	○	○	
		<45	×	(cold)	○(cold)	○(cold)	○(cold)	○(cold)	○(cold)	○(cold)	○(cold)	○(20°C)	○(80°C)	○(cold)	○(cold)	○(93°C)	○(93°C)	○	○	○	
		>45 75 conc.	△(30°C) △(hot)	○(30°C) △(hot)	x(cold)	○(cold)	×	○(cold) x(hot)	○(60°C)	○(60°C)	○(cold) x(hot)	○(85°C)	○(65°C)	○(65°C)	○(cold) ○(hot)	○(cold) ○(hot)	○(cold) ○(hot)	○(65°C)	x	○	
		100	×	x		○			○(60°C)	○		○	○			△	x	○			
		dryorwetm olten	○	○	○			x		○			○	○							
		(無水) (溶融)P ₂ O ₅																			
인산소다	NaH ₂ PO ₄ (나트륨)			○	○	○	○	x	○	○	○	○	○		○	○	○	○	○	○	
인산암모늄	(NH ₄) ₂ ·H ₂ PO ₄ (NH ₄) ₂ ·HPO ₄ (NH ₄) ₃ ·PO			○	○	○	○	x	○(60°C)	○	○	○	○	○(60°C)	○	○	○	○	○	○	
인산트리크질	(CH ₃ C ₆ H ₄) ₃ ·PO ₄			○							x	x				x	x	x	○	○	
잉크	-			○(20°C)	○(20°C)		○	x						○							
잿물	-			○	○	○	○		○	○	○	○	○		○	○	○	○	○	○	
전분	(C ₆ H ₁₀ O ₅) _n			○	○	○	○		○	○	○	○	○	○(60°C)	○	○	○	○	○	○	
전분액	-			○	○	○	○		○	○(60°C)	○	○	○	○	○(60°C)	○	○	○	○	○	
제라틴	-			○	○	○	○	○	○	○	○	○	○	○	○	○	○	○(93°C)	○	○	
제트연료	JP-5 JP-5			○(b.p)	○(b.p)	○(b.p)	○(b.p)	○	○(60°C)	○(60°C)		○	○		x	x	x	x	x	○	
주석	Sn	溶融 溶融 溶融	○(300°C) ○(400°C) x(600°C)	○(300°C) ○(400°C) ○(600°C)	○		x														
주석신	C ₆ H ₆ O	50	○(b.p)	○(b.p)	○(b.p)	○(b.p)	○	○	○	○	○(85°C)	○(25°C)	○	○(20°C)	○	○	○	×	○(93°C)	x	○
주석산칼륨	C ₆ H ₅ KO ₆	飽和	○(b.p)	○(b.p)										○							
중불산암모늄	NH ₄ FHF		x						○(60°C)	○	○		○			○	○	○	×	○	

천세산업주식회사

액명	분자식	농도(%)	금속					플라스틱(합성수지)						내마모재		고무					
			STS-304	STS-316	Ti(티타늄)	하스테로이C	Aluminum	PVC 영화비닐	PE 폴리에틸렌	PP 폴리프로필렌	PCTFE 3불화에틸렌	Teflon 테프론	PMMA 아크릴	족연(글루)	세라믹	CR 네오프렌	NBR 부니-N	CSM 하이파렌	EPDM E.P.R	FPM 바이톤	
증 아황산소다 (나트륨)	NaHSO ₄		○	○	△	△		○(60°C)	○	○	○	○		○	○	×	○	○	○	○	
증 크론산소다	Na ₂ Cr ₂ O ₇		○	○	○	△		○(60°C)	○	○		○	○(20°C)	×	○	△(93°C)	○	○(93°C)	○	○	
증 크롬산칼륨	KCr ₂ O ₇	10 25	○(b.p)	○ ○(b.p) ○(b.p)	○	△		○(60°C)	○	○(85°C)	△	○				○	○	○	○	○(25°C)	
증 탄산소다	NaHCO ₃		○	○	○	○		○(60°C)	○	○	○	○	○(60°C)	○	○	○(65°C)	○	○	○	○	
증 탄산수	H ₂ CO ₃			○		○(60°C)		○	○		○	○	○(60°C)		○	○	○	○	○	○	
증 탄산암모늄	NH ₄ HCO ₃		○	○					○	○	○	○	○			○	○	○	○	○	
증 탄산칼슘	KHCO ₃			○		○(60°C)		○	○		○	○	○(60°C)		○	○	○	○(93°C)	○	○	
증 황산소다 (나트륨)	NaHSO ₄		×	○	○	○(b.p)		○(60°C)	○	○		○	○(60°C)	○	○	○	○	○(93°C)	○	○	
증 황산칼슘	CaHSO ₄		×	○	○	○(b.p)		○(60°C)	○	○	○	○	○(60°C)		○						
증 류수	H ₂ O		○	○	○	○		○	○	○	○	○			○	○	○	○	○	○	
지방산	R-COOH	100 100	○	○(300°C)	○(100°C)	○(100°C)	○(230°C)	△	×	×	○(52°C)	○(85°C) ○(24°C) △(65°C)	○	○		○	○	×	○(90°C)	○	○
질간칼륨	KNO ₃		○	○	○	○	○	○(60°C)	○	○	○(160°C)	○	○(60°C)	○	○	○(73°C)	○	○	○	○	
질신산	HNO ₃	dil 5 10 30 ~30	○	○	○	○	×	○	×	○(23°C)	○(24°C)	○(25°C)	○(121°C) ○(b.p)	○(20°C) ×	○(121°C)	×	○	×	△(50°C)	○	○
		37 50	○(b.p)	○(b.p)	○(b.p)	○(b.p)	○(65°C) ×(b.p)	×	○	○	○	○	×	×	×	×	×	○		○	
질산니켈	Ni(NO ₃) ₂		○	○	○	○		○(60°C)	○	○	○	○	○(60°C)	○	○	○	○	○	○	○	
질산동	Cu(NO ₃) ₂		○	○	○	○	×	○(60°C)	○	○	○	○	○(60°C)	○	○	○(73°C)	○	○	○	○	
질산마그네슘	Mg(NO ₃) ₂		○	○	○	○		○(60°C)	○	○	○	○	○(60°C)	○	○	○	○	○	○	○	
질산반	Ba(NO ₃) ₂		○	○	○	○		○	○	○	○	○	○(60°C)	○	○	○	○	○	○(93°C)	○	
질산아연	Zn(NO ₃) ₂		○	○	○	○	×	○(60°C)	○	○	○	○	○(60°C)	○	○	○	○	○	○	○	
질산알미늄	Al(NO ₃) ₃		○	○	○	○		○(60°C)	○	○	○	○	○(60°C)	○	○	○	○	○	○	○	
질산암모늄	NH ₄ NO ₃		○	○	○	○		○(60°C)	○	○	○	○	○(60°C)	○	○	○(73°C)	○	○	○	○	
질산은	AgNO ₃	10	○	○	20% ○(52°C)	○	×	○(60°C)	○	○	○	○	○(60°C)	○	○	○	○	○	○	○	
질산제1수은	Hg ₂ (NO ₃) ₂		○	○	○	○		○(60°C)	○	○	○	○	○(60°C)	○	○	○	○	○	○	○	
질산제1철	Fe(NO ₃) ₂		○	○	○	○		○(60°C)	○	○	○	○	○(60°C)	○	○	○	○	○	○	○	
질산제2수은	Hg(NO ₃) ₂		○	○	○	○		○(60°C)	○	○	○	○	○(60°C)	○	○	○	○	○	○	○	
질산제2철	Fe(NO ₃) ₃		○	○	○	○	×	○(60°C)	○	○	○	○	○(60°C)	○	○	○(24°C)	○	○	○	○	
질산칼슘	Ca(NO ₃) ₂		○	○	○	○		○(60°C)	○	○		○	○(60°C)	○	○	○(65°C)	○	○	○	○	
질산프로필	C ₃ H ₇ NO ₂		○	○	○	○											×	○	○	×	
질신산	HNO ₃	conc. 30~60 70	△ ○(71°C) ×(110°C)	△ ○(71°C) ×(110°C)	△ ○(b.p)	○×(b.p)	△	×	×	×	×	○ △(25°C) ○(85°C)	○ ○(25°C)	○ ○(b.p)	×	○	×	×	×	△(24°C) ○△(38°C)	
질산나트륨	NaNO ₃		○	○	○	○		○(60°C)	○	○	○	○	○(60°C)	○	○	○(73°C)	○	○	○	○	
질산납	Pb(NO ₃) ₂		△	△	×	△									○	○					
질소	N		○	○										○		○	○			○	
차야염소산	HClO	20	×	×	○		×	○	×	△ △(40°C)				○	○	×	△	○	○		

천세산업주식회사

액명	분자식	농도(%)	금속					플라스틱(합성수지)						내마모재		고무					
			STS-304	STS-316	Ti(티타늄)	하스테로이C	Aluminum	PVC 영화비닐	PE 폴리에틸렌	PP 폴리프로필렌	PCTFE 3불화에틸렌	Teflon 테프론	PMMA 아크릴	족연(글루)	세라믹	CR 네오프렌	NBR 부니-N	CSM 하이파렌	EPDM E.P.R	FPM 바이톤	
차아염소산소다 (나트륨)	NaOCl	5 10 20 all%	△ △	△ △	○ ○	○ △		○(20°C) ○(20°C) ○(60°C)	○(20°C) △(25°C) △(25°C) x x	○ ○ ○(85°C) ○(6.25%)	○ ○(25°C)	○ ○(20°C) ○(20°C)	○ ○ ○(70°C)	○ ○ ○ ○(20°C)	○ ○ ○ ○	△ △ △	×	△ △	○ ○	○ ○	○ ○ △(70°C)
차아염소산칼륨	KOCl			x					○	○			○		○	x	×	△	○	○	
차아염소산칼슘	Ca(OCl) ₂	Cl ₂ 20	△	△	△	△	x	○(60°C) 12.5%	○	○(85°C) ○(6.25%)	30% ○(25°C)	○	○(20°C) 10%	○ ○(6.25%)	○ ○	x	×	○(93°C) △	○	○ ○ ○.25% x	
차아황산소다	NaHSO ₃		△	△		△	x			○		○		○	○ ○	○	○	○	○	○	
차염소산마그네슘	Mg(OCl) ₂			○					○	○		○		○	○ ○	○	○	○	○	○	
차황산소다 (나트륨)	NaSO ₃		○	○			x					○			○						
초산	CH ₃ COOH	dil 10 20	○△(b.p)	○△(b.p)	○(b.p)	○(80°C)	○	○ ○ ○	○ ○ ○	○ ○ ○	○ ○ ○	○ ○ ○	○ ○ ○	○(b.p) ○(b.p)	○(b.p) ○(b.p)	×	○(24°C) ○(60°C)	△	○	○ x	
		50 50 20~80 80		○			○	○ ○ ○	○ ○ ○	○ △ △ △	○ ○	○ ○	○ ○	○ ○	○ ○	x	△	×	○	○ x	
		conc. conc. 100	○△(b.p) △(b.p)	○△(b.p) ○(b.p)	○(b.p) ○(b.p)	○(80°C)	○	○ x x	△ x x	○ ○ ○	○ ○ ○	○ ○ ○	○ ○ ○	○(b.p) ○(b.p)	○(b.p) ○(b.p)	△	×	×	×	×	
초산	Cu(CH ₃ COO) ₂	wet	○(20°C)	○(20°C)																	
초산메틸 (디메칠에스테르)	CH ₃ COOCH ₃		○(b.p)	○(b.p)	○(b.p)	○(b.p)				○	○	○	○	x		×	○	×	×	×	
초산부틸	CH ₃ COOC ₄ H ₉		○(b.p)	○(b.p)	○(b.p)	○(b.p)				x	x	△	△	○	○(b.p) ○(b.p)	○(b.p) ○(b.p)	×	×	×	×	
초산소다 (나트륨)	CH ₃ COONa · 3H ₂ O		△	○	○	○		○	○	○	○	○	○		○(b.p)	○(b.p)	△	×	○	○	×
초산아밀	CH ₃ COO(CH ₃) ₂ CH ₃		○(b.p)	○(b.p)	○(b.p)	○(b.p)			x	x	○	△	x	○	○(b.p) ○(b.p)	○(b.p) ○(b.p)	×	×	×	×	
초산알루미늄	Al(CH ₃ COO) ₃			○									○		○	○	○	○	○	○	
초산암모늄	CH ₃ COONH ₄			○						○	○		○		○	○	○	○	○	○	
초산에틸	CH ₃ COOC ₂ H ₅		○(b.p)	○(b.p)	○(b.p)	○(b.p)			x	x	○	○	○	x	○(b.p) ○(b.p)	○(b.p) ○(b.p)	×	×	×	△	×
초산연	Pb(CH ₃ COO) ₂ · 3H ₂ O		○	○	○	○		○	△	○	○	○	○		○	○(b.p) ○(b.p)	×	×	○	○	
초산은	CH ₃ COOAg			○					○	○			○			○	×	○	○	○	
초산폴리비닐	CH ₃ COOCH=CH ₂		○	○	○	○			x	x			○			○	○	○	○	○	
차아염소산칼슘 (표백분)	Ca(ClO) ₂																				
치오시안화암모늄	NH ₄ SCN		○	○	○	○		○(60°C)	○	○	○	○	○(60°C)	○	○		○				
치오유산소다	Na ₂ S ₂ O ₃		○	○	○	○			○	○			○(60°C)	○	○	○	○	○	○	○	
카날릿트	MgCl ₂ +KCl	飽和	○(b.p)																		
카풀린산	C ₇ H ₁₅ CO ₂ H			○									○								
칼륨	K		△	△	○	○															
칼륨영반	Al ₂ (SO ₄) ₃ K ₂ SO ₄																				
케톤(각종)	R-O-R		○				△	x	x	x	△	○	x	×	○	x	×	×	x	x	x
코코너츠기름 (야자유)	—		○	○	○	○	○		○			○			○	○	○	○	△×(100°C)	×	○(100°C)
퀴노제	C ₆ H ₄ O ₂			○									○				x	○			
크레오솔트	—		△(hot)	△(hot)					x	○			○			x	△	×	x	×	○(24°C) × (100°C)
크레올	C ₆ H ₆ OHCH ₃		○	○	○(21°C)	○	△	○(40°C)	○(21°C)	○(20°C)	○(25°C)	○	×	(20°C)	○	○	△	○(24°C)	○(24°C)	○(24°C)	
크롬영반	Cr ₂ (SO ₄) ₃ K ₂ SO ₄																				

천세산업주식회사

액명	분자식	농도(%)	금속					플라스틱(합성수지)						내마모재		고무					
			STS-304	STS-316	Ti(티타늄)	하스테로이C	Aluminum	PVC 영화비닐	PE 폴리에틸렌	PP 폴리프로필렌	PCTFE 3불화에틸렌	Teflon 테프론	PMMA 아크릴	족연(글루)	세라믹	CR 네오프렌	NBR 부니-N	CSM 하이파렌	EPDM E.P.R	FPM 바이톤	
크롬 산 신	<chem>H2CrO4</chem>	10~60 dil dil	△(b.p)	△×(35~100°C)	○(b.p)	△	×	○(65°C)	○(24°C)	5%○(50°C) ○ ○	○(25°C)	○ ○	○(20°C) 10%	○ ○	○ ○	×	×	○(24°C)	○	○ ○	
		20			○(21°C)					○(25°C)	○	○	×(20°C)		○(40°C)	×	×	(14°C)	○ ×(70°C)	○(24°C)	
		40 50 conc.	△(b.p)	△×(35°C)	○(b.p)	△(30°C)	△(b.p)	○(50°C)	△(24°C)	×	×	○(121°C)		△ △ △	○ ○ ○	×	×	△		○	
크롬 산 칼 슘	<chem>K2CrO4</chem>		○	○	○	○			○	○	○	○	○	○ ○	○ ○	○	○	○	○	○ ○	
크실 렌	<chem>C6H4(CH3)2</chem>		△	○	○	○	○	×	×(22°C)	×	△	△	○(20°C)	○ ○	○ ○	×	×	×	×	○ ○	
클로로 로로 벤젠	<chem>C7H7Cl2</chem>		○	○	○	○			×	×		○	×		×	×	×	×	×	○	
클로로 로로 센	<chem>C14H18ClN3S</chem>			○								○	×			×					
클로로 로로 솔폰	<chem>SO2·OH·Cl</chem>		△	△(30°C)	○	△		○(22°C)	×	×	×	×	×	○ ○	○ ○	×	×	×	×	×	
클로로 포름	<chem>CHCl3</chem>		○(b.p)	○(b.p)	○(b.p)	○(b.p)	×	×	○(22°C)	○(20°C)	○(23°C)	○(25°C)	○	×	○ ○	○ ○	×	×	×	○(24°C)	
탄닌 산	<chem>C76H52O46</chem>	10	○	○	○	○	△	○(60°C)	○	○(85°C)		○		○ ○	○ ○	○ ○	×	○ ○	○ ○	○ ○	
탄산 산	<chem>H2CO3</chem>		○	○	○	○	△	○(60°C)	○	○		○	○	○ ○	○ ○	○ ○	○	○	○ ○	○ ○	
탄산 가스	<chem>CO2</chem>	dry wet	○ ○(482°C)	○ ○(482°C)	○ ○	○ ○(482°C)		○(60°C)	○ ○(60°C)	○ ○	○ ○	○ ○	○	○ ○	○ ○	○ ○	○ ○	○ ○	○ ○	○ ○	
탄산 동	<chem>CuCO3</chem>			×				○(60°C)	○	○	○	○	○(60°C)	○ ○	○ ○	○ ○	○ ○	○ ○	○ ○	○ ○	
탄산 마그네슘	<chem>MgCO3</chem>		○	○	○	○		○(60°C)	○	○	○	○	○(60°C)	○ ○	○ ○	○ ○	○ ○	○ ○	○ ○	○ ○	
탄산 바륨	<chem>BaCO3</chem>		○	○	○	○		○(60°C)	○	○(85°C)	○	○	○(60°C)	○ ○	○ ○	○ ○	○ ○	○ ○	○ ○	○ ○	
탄산 비스무스	<chem>BiCO3</chem>		○	○	○	○		○(60°C)	○	○	○	○	○(60°C)	○ ○	○ ○						
탄산 소다	<chem>NaCO3</chem>	10 飽和	○(b.p)	○(b.p)	○		×	○(73°C)	○(52°C)	○(100°C) ○(100°C)	○(25°C)	○(121°C)	○(60°C)	○ ○	○ ○	○ ○	○ ○	○ ○	○ ○	○ ○	
(소다화)	<chem>Na2CO3</chem>																				
탄산 암모늄	<chem>(NH4)2CO3</chem>		△(b.p)	△(b.p)	○	△		○(60°C)	○	○	○	○	○(60°C)	○ ○	○ ○	○ ○	○ ○	○ ○	○ ○	○ ○	
탄산 칼슘	<chem>K2CO3</chem>		○	○	○	○		○(60°C)	○	○	○	○	○(60°C)	○ ○	○ ○	○ ○	○ ○	○ ○	○ ○	○ ○	
탄산 칼슘	<chem>CaCO3</chem>		○	○	○	○	×	○(60°C)	○	○	○	○	○(60°C)	○ ○	○ ○	○ ○	○ ○	○ ○	○ ○	○ ○	
탄화수소	脂肪族 芳香族		○(b.p) ○(b.p)	○(b.p) ○(b.p)	○(b.p) ○(b.p)	○(b.p) ○(b.p)					○	○	△	○ ○	○ ○	○ ○					
테라핀 유	—		○	○	○	○	○		×	△						×	×	×	×	○	
토마토 쥬스	—		○	○	○	○		○	○	○	○	○	○(60°C)	○ ○	○ ○	○ ○	×	○ ○	○ ○	×	
톨루엔	<chem>C6H5CH3</chem>		○(b.p)	○(b.p)	○(b.p)	○(b.p)	○	×	×	×(20°C)	○(60°C) ○(85°C)	△(25°C)	○	×	○ ○	×	×	×(25°C)	×	×	○(24°C)
트리메틸아민	<chem>(CH3)3N</chem>		○(b.p)	○(b.p)	○(b.p)	○(b.p)		○(60°C)	×	○		○				○	×	○	○	×	
트리에탄올아민	<chem>N(C2H5OH)3</chem>		○	○	○	○		○(60°C)	×	○(100°C)		○			○	×	○	○	○	×	
트리클로로 (삼염화에틸렌)	<chem>C3HCl3</chem>						△														
트리토질인산염	<chem>C21H21O4P</chem>			○			△		×	○						×	×	×	×		
파라핀	<chem>CnH2n+2</chem>		○(b.p)	○(b.p)	○(b.p)	○(b.p)	○														
페클렌	<chem>KC2H2Cl4</chem>		○(b.p)	○(b.p)	○(b.p)	○(b.p)			×	×		○	×	○(20°C)	○ ○	×	×	×	×	○(38°C) ○(70°C) ×	
페프액	-검은액 -녹색액 -설파이트액 -크라프트액							○(66°C)	○(52°C)	○	○(121°C)	○		○	○	○	○	○	○		

천세산업주식회사

액명	분자식	농도(%)	금속					플라스틱(합성수지)						내마모재		고무				
			STS-304	STS-316	Ti(티타늄)	하스테로이C	Aluminum	PVC 영화비닐	PE 폴리에틸렌	PP 폴리프로필렌	PCTFE 3불화에틸렌	Teflon 테프론	PMMA 아크릴	족연(글루)	세라믹	CR 네오프렌	NBR 부니-N	CSM 하이파렌	EPDM E.P.R	FPM 바이톤
페 끄 액	- 히안액							○(66°C)	○(52°C)			○(121°C)		○		○				
페 끄 늘	H ₃ OH	conc.	△ ○	△ ○	○(21°C)	○	△	○(22°C) x(60°C)	△	○(70°C)	○(160°C)	○ ○	x	○	×	×	×	○(100°C) △(150°C)		
페리시안화소다 (나트륨)	Na ₃ [Fe(CN) ₆] Na ₄ [Fe(CN) ₆]		○	○	○	○		○(60°C)	○	○	○	○(60°C)		○	○	○	○	○	○	
페 리 시 안 화 칼 텐	K ₃ [Fe(CN) ₆]		○	○	○	○		○(60°C)	○	○	○	○(60°C)		○	○	○	○	○	○	
포 도 당	C ₁₆ H ₁₂ O ₆		○	○	○	○		○(60°C)	○	○	○	○(60°C)		○	○	○	○	○	○	
포 도 산	-		○	○	○	○		○	○	○	○	○(60°C)		○	○	○	○	○	○	
포 도 주	-		○	○	○	○	x	○(60°C)	○	○(85°C)	○	○	○	○	○	○	○	○	○	
포 름 알 데 히 드 (모 르 말 린 <40%)	HCHO	37 >37 40	○ x ○	○(b.p) ○	○	○	○	○(60°C)	○	○(26°C) △(85°C)	○(90°C)	○(121°C) ○ ○	○(20°C) 40%	○	○	×	×	△ ○ △		
표 백 분	Ca(ClO) ₂																			
푸 린	C ₄ H ₄ O			○							△(25°C)	○				×	×		×	×
프 레 온	CCl ₂ F ₂	TF 11 12	○ ○ ○	○ ○ ○	○ ○ ○	○ ○ ○		○(22°C) ○(22°C)	△ △ △		○ ○			○	○	×	(24°C) ○(24°C)	○ ×	○ △(24°C)	
		22 113 114	○ ○ ○	○ ○ ○	○ ○ ○	○ ○ ○			△ △ △	○(25°C)	○ ○ ○			○	○	○(24°C)	○ ○ ○	×	○(24°C) △(24°C) △(24°C)	
프로판(물) (프로필알콜)	C ₃ H ₇ OH		○	○	○	○	○	○(60°C)	○	○(85°C)		○(121°C)	x			○	○	○	○(24°C)	
프로피온산	C ₂ H ₅ COOH		○	○	○	○														
프루프릴알코올	C ₄ H ₁₀ CHO		○	○	○	○				○(70°C)	○(25°C)	○(121°C)				x	x	△	×	
프 탈 신	C ₆ H ₄ (COOH) ₂		○	○	○	○					○				○					
프로카를	C ₆ H ₃ (OH) ₃		○(20°C)	○(20°C)		○									○					
프리딘	C ₅ H ₅ N		○	○	△	○		○		○	○			○	○					
프 마 자 유	-		○	○	○	○	x	×	○(22°C)	○	○	○(25°C)	○			○	△	○	△	
프 크 린 신	C ₆ H ₃ O ₇ N ₂		○	○		○	x								○	○	△	○	○	
하 수	-	Cl ₂ 飽和		×	(93°C)															
해 수	-		△	△	○	○	△		○(40°C)	○	○	○(b.p)	○(60°C)	○	○	○	○	○	○	
행 내 수	-	酸性	○	○		○				○	○	○		○	○	○	○	○	○	
현 신	C ₆ H ₁₄		○(b.p)	○(b.p)	○(b.p)	○(b.p)	○	○(22°C)	×	×	○	×	(20°C)		○	△(24°C)	○	×	○(24°C)	
현 산 물	C ₆ H ₅ OH		○(b.p)	○(b.p)	○(b.p)	○(b.p)	○	○(60°C)	△	○(20°C)		○(121°C)	x			○	○	△	○(80°C)	
현 탄	C ₇ H ₁₆		○	○	○	○	○	○(60°C)	×	○(26°C) △(85°C)	○(25°C)	○			○	○	△	○	×	
활 액	-			○					○	○						○				
황 신	H ₂ SO ₄ ← H ₂ SO ₄ ← HNO ₃ ← 酸←	>15 <15 <15 <1	×	×	×	○	○	×			○	○		×	○					
황 신	H ₂ SO ₄	5 5 5 <10	○(20°C) △(35°C) x(b.p) x	○(20°C) △(35°C) x(b.p) ○	○	○	△(b.p) △(b.p)	○	○(60°C)	○(60°C)		○(100°C)	○(b.p) ○	○(20°C)	○	○	×	○	○	
		50 50 0~60	×	×	×	△(b.p)	○(65°C) x(b.p)	×	○(50°C)	△(50°C)	△(50°C)			×	(20°C)	○	△	×	○(141°C)	○(121°C)
		10~75 50~85 80	×	×	×	×	○(55°C)		○(60°C)	○	×	○(25°C)	○(121°C)			○	×	×	○(70°C)	○



천세산업주식회사

액명	분자식	농도(%)	금속					플라스틱(합성수지)					내마모재		고무					
			STS-304	STS-316	Ti(티타늄)	하스테로이C	Aluminum	PVC 영화비닐	PE 폴리에틸렌	PP 폴리프로필렌	PCTFE 3불화에틸렌	Teflon 데프론	PMMA 아크릴	흑연(광물)	세라믹	CR 네오프렌 부나-N	NBR 부나-N	CSM 하이파伦	EPDM E.P.R	FPM 바이탈
황산 산 발 煙		75~95 95 95	x	x	x	x(b.p)	x	○	x	△(25°C) △(85°C)		○		○ x x	x			○		
		85~96 98 98	○(20°C) x(100°C)	○(20°C) x(100°C)	x(b.p)	○(65°C) x(b.p)	x	○(60°C) ○(55°C) △(60°C)	x ○(50°C) △(55°C)	△ △(55°C)	○(100°C)	○ ○		△ x x	○ x ○	x x	○ △(44°C)	x ○ ○(70°C)		
		conc. conc. 發煙→98	○(cold) x(hot)	○(cold) x(hot)	x x x	○(cold) x(hot)	x	○(cold)		△(20°C)		○(cold) ○(hot) ○		○(cold) x	○(cold) ○	x x x		△(cold) x		
		H ₂ SO ₄ (SO ₃ 우리끼)	(115)20		x			△		x	×(26°C) ×(85°C)	○(25°C)	○			x x	x x	○	x ○(24°C)	
황산니켈	NiSO ₄		△	△	x	△		○(60°C)	○	○	○	○	○(60°C)		○ ○	○(73°C)	○ ○	○ ○	○ ○	
황산동	SuSO ₄	飽和	△	△	△	○		○(60°C)	○	○(55°C)	○(160°C)	○	○(60°C)		○ ○	○ ○	○(65°C)	○ ○	○ ○	
황산디메릴	(CH ₃ O) ₂ SO ₂		○	○	○	○									x ○	x x	△ x		x	
황산마그네슘	MgSO ₄		△	△	○	△	△	○(60°C)	○	○(85°C)	○	○	○(60°C)		○ ○	○ ○	○(72°C)	○ ○	○ ○	
황산바륨	BaSO ₄		○	○	○	○		○(60°C)	○	○(85°C)	○	○	○(60°C)		○ ○	○ ○	○ ○	○ ○	○ ○	
황산소다	NaSO ₄		△	△	○	○	△	○(60°C)	○	○	○(150°C)	○	○(60°C)		○ ○	○ ○	○ ○	○ ○	○ ○	
황산수소나트륨	NaHSO ₄	飽和	△	△	○	○		○	○	○(55°C)	○	○	○		○ ○	○ ○	○ ○	○ ○	○ ○	
황산아연	ZnSO ₄		△	△	○	○(55°C)	x	○(60°C)	○	○(85°C)	○(125°C)	○			○ ○	○ ○	○ ○	○ ○	○ ○	
황산알루미늄	Al ₂ (SO ₄) ₃	飽和	○	○	○	○		○(60°C)	○(55°C)	○(55°C)	○(125°C)	○			○ ○	○ ○	○(20°C)	○ ○	○(121°C)	○ ○
황산알루미늄·칼륨	Al ₂ (SO ₄) ₃ K ₂ SO ₄																			
황산암모늄	(NH ₄) ₂ SO ₄		○	○	○	○	x	○(60°C)	○	○	○(160°C)	○	○(60°C)		○ ○	○ ○			○(93°C)	
황산암모늄·마그네슘	(NH ₄) ₂ SO ₄ MgO			○	○	○			○	○		○	○(60°C)		○ ○	○ ○	○ ○	○ ○	○ ○	
황산제이수은	HgSO ₄			○					○(60°C)	○	○	○	○(60°C)					○(72°C)		
황산제이철	Fe ₂ (SO ₄) ₃		△	△	△	△	x	○(60°C)	○	○	○	○	○(60°C)		○ ○	○ ○	○(72°C)	○ ○	○ ○	
황산제일철	FeSO ₄		△	x	○	△	x	○(60°C)	○	○	○	○	○(60°C)		○ ○	○ ○		○ ○	○ ○	
황산칼륨	K ₂ SO ₄		○	○	○	△		○(60°C)	○	○	○	○	○(60°C)		○ ○	○ ○	○(73°C)	○ ○	○ ○	
황산칼슘	CaSO ₄		○	○	○	△	x	○(60°C)	○	○	○	○	○(60°C)		○ ○	○ ○		○ ○	○ ○	
황산크롬·칼슘 (명반)	Cr ₂ (SO ₄)K ₂ SO ₄																			
황열	K ₄ [Fe(CN) ₆] · 3H ₂ O								○(60°C)											
황하칼슘	K ₂ S		○	○	○	○		○		○	○	○			○ ○	○ ○	○ ○	○ ○	○ ○	
황화물폐액	-								○		○					○ ○	○ ○	○ ○	○ ○	
황화바륨	BaS		○	○	○	○	x		x ○(60°C)	○	○	○			○ ○	○ ○	○(73°C)	○ ○	○ ○	
황화소다	Na ₂ S		○	○	○	○		○(60°C)	○	○	○(25°C)	○			○ ○	○ ○		○ ○	○(93°C)	
황화수소	H ₂ S	dry wet	x x	○ ○	○ ○	○ △		○(60°C) ○(60°C)	○	○	○(121°C) ○(121°C)			○ x ○	○ x ○	○ x	○ ○	○ ○		
황화암모늄	(NH ₄) ₂ S									○	○	○								
히드랄라진	N ₂ H ₄		○	○	○	○			x	x		○								
SAE	#10								○	○		○				x	○ x	○ x	○ ○	